


**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup>:</b> <b>B65D 39/00</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 96/34806</b> <b>(43) International Publication Date:</b> 7 November 1996 (07.11.96)
<b>(21) International Application Number:</b> PCT/GB96/01065 <b>(22) International Filing Date:</b> 3 May 1996 (03.05.96)  <b>(30) Priority Data:</b> 9508972.8 3 May 1995 (03.05.95) GB 9607815.9 10 January 1996 (10.01.96) GB  <b>(71)(72) Applicants and Inventors:</b> TAYLOR, David, Graham [GB/GB]; 37 Linersh Wood Road, Bramley, Guildford, Surrey GU5 0EE (GB). BEANLAND, David [GB/GB]; 2 Halfway Cottages, Dippenhall, Farnham GU10 5DR (GB).  <b>(74) Agent:</b> BAVERSTOCK, Michael, George, Douglas; Boulton Wade Tennant, 27 Fumival Street, London EC4A 1PQ (GB).		<b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> CLOSURE DEVICE FOR CONTAINERS  <b>(57) Abstract</b> <p>A closure device for a container such as a wine bottle comprising a body (1) of circular cross section, preferably cylindrical, which is adapted to fit in an opening in the container to seal said container said body consisting essentially of a moulded foamed closed-cell polymer of copolymer, preferably expanded polystyrene, having a substantially uniform density of at least 0.03 g/cc. The closure device may be partially or wholly coated with a sealing material (5), waxed, coloured and/or surface-treated to render it even closer in appearance to cork, and printed on.</p> 		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgystan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

CLOSURE DEVICE FOR CONTAINERS

This invention relates to a closure device for containers.

5        Closure devices for containers are commonly made of natural materials such as cork. These are used for temporarily sealing containers in order to prevent spillage and to preserve the contents of the container. They have a traditional appeal and are effective. Very large quantities are used in wine  
10       bottling and they are also used for other foodstuffs and for other substances such as cosmetics. However, they have the disadvantage of being relatively expensive, are labour intensive to produce, are  
15       subject to quality variations and can introduce microorganisms and other impurities to the stored substance. These disadvantages have been recognised for some time and synthetic substitutes have been developed using synthetic rubbers and plastics.  
20       These, however, have the disadvantages of being more expensive than natural materials, of not being readily reusable, of not looking and feeling like natural materials and of behaving differently to the natural materials. Consumers notice these differences and are  
25       put off, thus reducing the acceptability of these substitutes in the marketplace. There is thus a need for a synthetic closure which looks, feels and behaves similarly to the natural material but with advantages of low cost, consistent quality, and of being sterile.  
30       In EP-A-0 496 194 there is described and claimed a sealing closure for containers of liquids characterised in that it comprises a substantially cylindrical plastic element, which may be made of foamed polystyrene, in which an also substantially  
35       cylindrical elastic insert, which may be of cork, is

- 2 -

axially embedded. However, such a design of closure appears potentially to have serious drawbacks from the point of view of lack of sterility due to the presence of the natural cork; from the point of view of structural integrity; and from the point of view of inadequate elastic behaviour. Also, although it is stated in the description of the patent specification that the production cost will be low, the complex structure of the product would indicate the contrary.

There is therefore still a demand for a satisfactory alternative to cork closures for containers, and particularly for liquid containers such as wine bottles.

According to the present invention there is provided a closure device for a container comprising a body of circular cross-section which is preferably cylindrical and which is adapted to fit in an opening in the container to seal said container said body consisting essentially of moulded foamed closed-cell polymer or copolymer preferably expanded polystyrene, having a substantially uniform density of at least 0.03 g/cc.

It should be noted that the closure device of the invention does not contain an insert of any other material in its body.

The particularly preferred polymeric material of the closure device of this invention is expanded polystyrene. Expanded polystyrene is well known for its very low density and it is extensively employed, for example, in packaging applications in which the expanded polystyrene used may typically have a density of 0.016 g/cc. It is important to note, however, that an essential novel feature of the present invention is that the polymeric material used has a density of at least 0.03 g/cc so that it is more comparable in

- 3 -

density to cork which typically has a density of around 0.1 g/cc although varying depending its source. Also the increased density of the material renders it more impermeable to gases and liquids. Thus, the  
5 process conditions used for the production of moulded expanded polystyrene closure devices of the present invention are controlled, in known conventional manner, to produce a final density of at least 0.03 g/cc.

10 Although the preferred shape of the body of closure device in accord with the invention is substantially cylindrical it may for example be of other shapes having a circular cross-section, for example frustoconical. Also, the closure device may  
15 have an enlarged end, that is an end which has a larger diameter than the body of the closure device, similar to that of the types of cork which are used for sealing wines of the "Champagne" type in which the enlarged end serves to provide an anchorage for a wire  
20 fastening attached to the neck of the bottle to secure the closure device against being forced out of the mouth of the bottle by the internal pressure of the gas in the bottle.

The closure device of the invention is inserted  
25 into the opening of a container to prevent the material held in the container escaping through the container's opening when the closure is in place. It also prevents outside contaminants such as gases, moisture, bacteria or fungi from entering the  
30 container through the opening. Through achieving an air-tight seal, it maintains the material stored in the container in as near perfect a condition as possible.

The polymeric material of the closure is  
35 desirably coloured to look like the natural material

that it replaces and is also desirably surface-textured or otherwise physically surface-treated with the same end in view. It can also be painted and/or be printed with information on its surface if  
5 required.

The closure may be pressure treated in its manufacture for example by rolling. It was originally thought that this pressure treatment increased both the elasticity and the density of only a surface layer  
10 of the material. However it is now believed that the pressure treatment increases the elasticity and density of the whole body of the closure but that there is no significant resulting change in the uniformity of its density. This pressure treatment  
15 enhances the closure's ability to press against the walls of the container opening and thereby to seal it.

The closure may also be coated with a flexible impervious coating such as polyurethane if an additional degree of impermeability is required. The  
20 closure may also be waxed. Additionally, any coating composition used may contain colour so as to render the closure device of similar colour to that of natural cork.

A specific embodiment of the invention will now be described by way of example with reference to the  
25 accompanying drawing in which:

Figure 1 shows a perspective of the closure device, in this case acting as a substitute for a cork in a wine bottle.

30 Figure 2 shows the closure device in place in a wine bottle.

Referring to the drawings, the closure device comprises a cylinder of expanded polystyrene 1 of substantially uniform density greater than 0.03 g/cc.  
35 At such higher densities, the expanded polystyrene

- 5 -

exhibits a greatly reduced permeability to gases and water vapour, and to other fluids. Expanded polystyrene is resistant to alcohol and is an approved material for contact with foodstuffs. It is

5 biologically inert and acts as a barrier to the ingress of bacteria and moulds. Also, as mentioned above, at higher densities such as above 0.03 g/cc it also compares favourably to cork in density and also has a microstructure of similar appearance to that of

10 cork. The texture of its external surface 2 is already very cork-like and this is desirably enhanced by colouring and/or by physically treating the surface, for example by shaving, sanding or texturing. The frictional properties between high density

15 expanded polystyrene and glass compare favourably to those between cork and glass. It should be noted however that cork relies to some extent on absorption of liquid from the contents of the container in order to achieve its effectiveness in sealing whereas the

20 closure device of the present invention does not absorb liquids to any significant degree.

As is well known in the art, expanded polystyrene is conventionally produced by a bead process using a suspension polymerisation technique. A blowing agent

25 such as for example about 6% of a low boiling petroleum ether fraction, e.g. n-pentane, is either incorporated before polymerisation, or after polymerisation the beads are impregnated under heat and pressure. The beads are then processed by steam

30 moulding. The beads are first pre-foamed by heating in a steam bath. This causes the beads to expand and the expansion is continued until they reach an appropriate level in the mould corresponding to the desired density. This may be determined by a suitably

35 positioned thermocouple which is arranged to cause the

- 6 -

steam to be switched off when this point is reached.  
The expanded beads are then allowed to stand for 24  
hours to allow them to cool to room temperature and to  
allow air to diffuse into the cells so that the cells  
5 equilibrate with outside conditions.

Then a steam moulding process is performed. The  
beads are charged into a mould which is provided with  
perforated walls to admit steam. The mould is  
completely filled with the beads. Steam is then  
10 passed into the mould causing the beads to swell  
further and to weld with each other and take up the  
shape of the mould.

When the bodies of the closure devices are to be  
substantially cylindrical the mould itself may be in  
15 the form of a plurality of cylinders which may be  
interlinked each of which cylinders may be several  
times the length of the closure devices to be  
produced.

When moulding is complete the mouldings are taken  
20 out of the moulds, trimmed, cut to length, printed,  
textured, coated and waxed with paraffin wax, as  
appropriate.

It should be understood of course that the above-  
mentioned specific procedure can be varied in many  
25 respects without departing from the scope of the  
invention as hereinafter claimed.

The resulting closure devices can be inserted  
directly into a container such as a bottle at this  
stage if the mouldings are of sufficiently small  
30 diameter. However, for greater pull strengths larger  
diameter mouldings are used which are reduced in size  
by compression, e.g. by rolling, before being put into  
a conventional cork inserter.

It should be mentioned that because expanded  
35 polystyrene does not have the same elasticity as cork



- 7 -

it is usually necessary to adjust conventional cork inserters from a usual diameter of 16 mm for a conventional cork closure to a diameter of say 18 mm for the closure device of the present invention, to  
5 allow for this difference in elasticity and corresponding expansion.

As mentioned above, the closure device may be pressure treated, for example by rolling, to improve the elasticity of the polystyrene. The closure device  
10 is compressed as it is pushed into a bottle 3 and provides a seal against the glass. On withdrawal the elasticity of the closure device creates a good simulation of the sensation of a real cork being removed from a bottle and allows the closure device to  
15 be reinserted if required. The closure device retains rigidity thus providing mechanical strength to prevent the closure device from distorting through bending when it is pushed into a bottle 4 and to provide purchase for extraction devices. The high density  
20 expanded polystyrene is practically impervious to gases and fluid of the nature likely to be encountered in wine. Additional protection can be given by treating the ends and/or sides with a colourless impermeable coating such as polyurethane 5.

25 As explained above, therefore, the closure device of the invention thus consists essentially solely of an expanded closed-cell polymer, preferably expanded polystyrene, which has a substantially constant density of greater than 0.03 g/cc throughout, and  
30 which can be partially or wholly surface coated with an impermeable sealing material for example with polyurethane and/or a wax to prevent moisture and gaseous movement through and around the closure device.

35

CLAIMS:

1. A closure device for a container comprising  
a body of circular cross-section which is adapted to  
fit in an opening in the container to seal said  
container said body consisting essentially of a  
moulded foamed closed-cell polymer or copolymer having  
a substantially uniform density of at least 0.03 g/cc.
2. A closure device as claimed in claim 1  
wherein the foamed closed-cell polymer or copolymer is  
expanded polystyrene.
3. A closure device as claimed in claim 1 or  
claim 2 wherein said body is substantially  
cylindrical.
4. A closure device as claimed in any one of  
the preceding claims wherein the foamed polymer or  
copolymer is coloured so as to render the closure  
device of similar colour to that of natural cork.
5. A closure device as claimed in claim 1 or  
claim 2 having a surface which is partially or wholly  
coated with a sealing material, for example a  
polyurethane resin and/or with wax, which may contain  
colour so as to render the closure device of similar  
colour to that of natural cork.
6. A closure device as claimed in any one of  
the preceding claims whose surface has been physically  
treated, for example by shaving, sanding or texturing,  
to bring its appearance closer to that of natural  
cork.

- 9 -

7. A closure device as claimed in any one of the preceding claims which is painted and/or has printed matter on its surface.

5        8. A closure device as claimed in any one of the preceding claims which is for use in wine bottles.

10       9. A method of making a closure device for a container which method comprises steam moulding expanded polystyrene beads in one or more cylindrical moulds having a diameter substantially corresponding to the diameter of the closure devices to be produced, the steam moulding process being performed under conditions such that a density of at least 0.03 g/cc  
15       is uniformly produced in the mouldings, the mouldings being thereafter removed from the moulds and then, if necessary, the mouldings are trimmed and cut to the desired length of the closure device, and, if desired, the mouldings are partially or wholly coated with a  
20       sealing material, for example a polyurethane resin, and/or with wax either before or after the optional cutting to size.

25       10. A method as claimed in claim 9 wherein the mouldings are subjected to compression by rolling under pressure in order to reduce their diameter.

30       11. A container, either empty or when containing a liquid or a solid, whenever comprising a closure device as claimed in any one of claims 1 to 8 or when made by the method claimed in claim 9 or claim 10.

Fig 1





Fig 2



## INTERNATIONAL SEARCH REPORT

International Application No  
PCT/GB 96/01065

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 B65D39/00

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B65D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US,A,4 091 136 (O'BRIEN ET AL) 23 May 1978	1,3-5,8,
Y	see claims 1,3	11
A	see column 4, line 37 - line 38	2,7
Y	EP,A,0 496 194 (FANTIN) 29 July 1992 cited in the application see abstract	9
Y	WO,A,94 25513 (SUPREME CORQ) 10 November 1994	2
A	see abstract; figure	7
A	US,A,4 668 557 (LAKES) 26 May 1987	1,8

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- \*&\* document member of the same patent family

Date of the actual completion of the international search

20 August 1996

Date of mailing of the international search report

26.08.96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax (+31-70) 340-3016

Authorized officer

Smith, C

## INTERNATIONAL SEARCH REPORT

Information on patent family members

Application No

PCT/GB 96/01065

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-4091136	23-05-78	NONE	
EP-A-496194	29-07-92	IT-B- 1247147	12-12-94
		DE-D- 69202065	24-05-95
		DE-T- 69202065	15-05-96
		ES-T- 2073785	16-08-95
WO-A-9425513	10-11-94	US-A- 5496862	05-03-96
		AU-B- 6783894	21-11-94
		BR-A- 9406394	13-02-96
		CA-A- 2161673	10-11-94
		CZ-A- 9502880	14-02-96
		EP-A- 0698054	28-02-96
		FI-A- 955287	03-01-96
		HU-A- 73270	29-07-96
		NO-A- 954417	03-01-96
		PL-A- 311642	04-03-96
		US-A- 5480915	02-01-96
US-A-4668557	26-05-87	AU-B- 610505	23-05-91
		AU-B- 7512987	10-02-88
		CA-A- 1316310	20-04-93
		EP-A- 0328518	23-08-89
		JP-T- 2500894	29-03-90
		WO-A- 8800523	28-01-88